

Woven Geotextile ASTM Test

Property	Test Method	Marv English		
Grab Tensile	ASTM D-4632	200 lbs	250 lbs	315 lbs
Grab Elongation	ASTM D-4632	15%	15%	15%
Mullen Burst	ASTM D-3786	400 psi	450 psi	600 psi
CBR Puncture Strength	ASTM D-6241	700 lbs	750 lbs	900 lbs
Trapezoidal Tear	ASTM D-4533	75 lbs	90 lbs	125 lbs
UV Resistance(500hrs)	ASTM D-4355	70%	70%	70%
Permittivity	ASTM D-4491	0.05-sec ⁻¹	0.05-sec ⁻¹	0.05-sec ⁻¹
AOS	ASTM D-4751	0.425 mm	0.425 mm	0.425 mm
Flow Rate	ASTM D-4491	5 Gal/min/sq ft	4 Gal/min/sq ft	4 Gal/min/sq ft



Phone: +8615688411080

Email: info@qivoc.com

Address: 1-2306 Meilian Plaza, Jinan City, Shandong Province, China

Website: qivoc.com